

SabreFix™ PU 30 MIN



SabreFix PU 30 min is a one component, waterproof thixotropic polyurethane adhesive which cures by reaction to the moisture in the substrates. Dry porous materials usually contain sufficient moisture in order to create the vulcanization. SabreFix PU complies with the D4 standard, DIN 68602.

Applications

SabreFix PU 30 min is suitable for bonding dry and moist wood (max. 30%), rubber, foam rubber, P.U. foam, concrete, glass wool, all porous materials.

Properties

Basis	Prepolymer P.U.: reacting to humidity
Viscosity	Thixotropic paste
Colour	White
Dry matter	+/- 100%
Gravity	1.12 g/cm ³ + or - 0.01 g/cm ³
Temperature resistance	-30°C to + 100°C
Resistance to water	D4-standard, DIN 68602
Resistance to chemicals	List on request
Clamp time	At 15°C to 20°C: 30 min handresistant

Surfaces

- 1 Materials to be bonded must be clean and free from grease.
- 2 Non porous materials should be slightly abraded.
- 3 Components must be bonded within 10 mins.
- 4 Pressing or clamping joints will ensure final bond strength.

ATTENTION: components may be moved 1 hours after bonding. It is essential that at least one of the components to be bonded is porous and contains moisture.

Precautions

- Contains polyisocyanates
- Noxious
- Avoid temperatures above 35°C
- Wear gloves
- Harmful by inhalation
- Irritating to eyes, respiratory system and skin
- Keep out of reach of children
- In case of contact with eyes, rinse abundantly with water and consult a physician
- After contact with skin, wash with plenty of water and soap
- Use in well ventilated areas, if insufficient, wear respiratory protection
- In case of accident, consult a physician

Consumption

250 to 450 g/m² depending on the application.

Processing Time

10 minutes.

Application Temperature

From +5°C to +35°C.

Storage & Shelf Life

Min. 12 months in original packing in a dry and cool place between +5°C and +25°C.

Packaging & Colour



Available colours: Natural

Packaging size: 310ml Cartridges

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.

New Zealand

+64 6 366 0007
40-42 Cambridge St South
Levin 5510

Melbourne

+61 3 8657 5507
67 Gateway Blvd
Epping, VIC 3076

Sydney

+61 2 9098 8244
Level 6, 10 Herb Elliott Ave
Sydney Olympic Park, NSW 2127